

### Eco Solvent Poly Cotton Canvas 370gsm Canvas Range IFA 96

#### Product Description

Bright white semi-gloss poly cotton inkjet canvas with eco solvent, latex and UV ink compatible coating.

#### Features

- Bright white
- Eco solvent, latex and UV ink compatible
- Fast drying
- Scratch resistant coating, waterproof
- Poly cotton mix
- High level of crack resistance
- Heavyweight, textured surface

#### Applications

- Fine art and photographic open and limited edition prints for the décor art market
- Fine art reproduction prints for interior imaging
- Stretched canvases and gallery wraps

Basic Weight (gsm)	370		
Canvas Thickness (Microns)	500	Canvas Thickness (Inches)	0.019
Base Material	Poly Cotton		
Coating Type	Semi-Gloss		
Ink Type	Eco Solvent, UV and Latex		
Surface Texture	Canvas		
Whiteness (CIE)	>95		
Brightness (TAPPI)	95.6		
OBA Content	Yes		
pH	7.5		
Recyclable	Yes		
Print Settings*			
Notes			

Sheets	
Rolls (25m/82ft Length)	60", 54", 30"

Additional Sizes are available on request, subject to order quantity.

#### Handling and Storage

- All digital Fine Art Papers and Canvases are fragile and need to be handled with extreme care. Try not to touch the surface of the paper, always hold the paper by the edges and wear cotton gloves if necessary.
- Return unused material to the original box and only store finished prints in archival quality packaging. If mounting or framing, use only archive grade tapes and glues.
- After printing, leave prints open to the air to fully dry (24 hours is recommended). Do not stack prints on top of each other straight away.
- Using a giclée varnish or spray will help protect your print from damage, effects of UV light and environmental attack.

#### Conditions of Use

- The recommended climate for storage of all papers is 15-20°C, relative humidity of 40-60%. Always store in original packaging, out of direct sunlight and protected from moisture.
- Do not exceed temperatures of 82°C (180°F) when dry mounting.

All recommendations are for your guidance only. These are subject to our test criteria, which remain subject to change without prior notice.